

Attorney Docket No. 01634/LH

Express Mail Mailing Label
No.: EL 874 117 051 US

**IN THE UNITED STATES PATENT
AND TRADEMARK OFFICE**

Date of Deposit: October 9, 2001

Applicant(s): K. MITANI et al

Serial No. :


Filed : Herewith

For : GLASS SUBSTRATE FOR
INFORMATION RECORDING
MEDIA AND MANUFAC-
TURING METHOD THEREOF

Art Unit :

Examiner :

I hereby certify that this paper is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Asst. Commissioner for Patents, Washington, D.C. 20231


Barbara Villani

In the event that this Paper is late filed, and the necessary petition for extension of time is not filed concurrently herewith, please consider this as a Petition for the requisite extension of time, and to the extent not tendered by check attached hereto, authorization to charge the extension fee, or any other fee required in connection with this Paper, to Account No. 06-1378.

Asst. Commissioner for Patents
Washington, D.C. 20231

PRELIMINARY AMENDMENT

S I R :

Please amend the claims as follows:

11. **(amended)** A glass substrate for an information recording medium manufactured using the method claimed in claim 1, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

12. **(amended)** A glass substrate for an information recording medium manufactured using the method claimed in claim 1, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

Please add claims 13-30 as follows:

--13. (new) A glass substrate for an information recording medium manufactured using the method claimed in claim 2, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

14. (new) A glass substrate for an information recording medium manufactured using the method claimed in claim 3, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

15. (new) A glass substrate for an information recording medium manufactured using the method claimed in claim 4, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

16. (new) A glass substrate for an information recording medium manufactured using the method claimed in claim 5, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

17. (new) A glass substrate for an information recording medium manufactured using the method claimed in claim 6, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

18. (new) A glass substrate for an information recording medium manufactured using the method claimed in claim 7, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

19. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 8, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

20. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 9, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

21. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 10, wherein a bearing height EH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

22. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 2, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

23. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 3, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

24. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 4, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

25. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 5, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

26. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 6, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

27. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 7, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

28. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 8, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.

29. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 9, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.


30. **(new)** A glass substrate for an information recording medium manufactured using the method claimed in claim 10, wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.--

R E M A R K S

A copy of the page of the original application containing the marked-up claims is attached hereto (we amended claims 11 and 12) with the amendments handwritten thereon.

The present amendment removes all multiple dependent claims without changing the scope of coverage.

Respectfully submitted,



LEONARD HOLTZ
Reg. No. 22,974

Frishauf, Holtz, Goodman, Langer & Chick, P.C.
767 Third Avenue - 25th Floor
New York, New York 10017-2023
(212) 319-4900

Fax No. (212) 319-5101

LH/bv

surface of the glass substrate that has been subjected to the surface scrubbing to chemical strengthening.

10. A method as claimed in claim 1, further comprising the step of subjecting texturing and chemical strengthening in this order to the at least one surface of the glass substrate before the surface scrubbing is carried out on the at least one surface of the glass substrate.

11. A glass substrate for an information recording medium manufactured using the method claimed in ^{claim 1} [any one] of claims 1 through 10], wherein a bearing height BH04 of at least one surface of the glass substrate at which a contact ratio is 0.4% as measured using an atomic force microscope is in a range of 2 to 7 μ m.

12. A glass substrate for an information recording medium manufactured using the method claimed in ^{claim 1} [any one] of claims 1 through 10], wherein a bearing height BH01 of at least one surface of the glass substrate at which a contact ratio is 0.1% as measured using an atomic force microscope is in a range of 2 to 10 μ m.